

ZHENGZHOU HAIXU ABRASIVES CO.,LTD
EMAIL:SALES@ZZHAIXU.CN
MP/WECHAT/WHATSAPP:+8615838373120
WEBSITE:<http://chinasic.net>

TECHNICAL DATA SHEET

PRODUCT: GC GREEN CARBORUNDUM

SIZE:F46

GC Green Carborundum is produced in electrical internal resistance furnaces from silica sands and petroleum coke(added salt during smelting),with high hardness,thermal conductivity and strength.

AVERAGE CHEMICAL COMPOSITION(TYPICAL)

SiC	≥98.6%
C _F	≤0.20%
Fe ₂ O ₃	≤0.40%
SiO ₂	≤0.05%

PHYSICAL PROPERTIES(TYPICAL)

Density	≥3.18g/cm ³
Mohs Hardness	9.4
Magnetic	≤0.0017%
Melting Point	2250°C
Refractoriness	1900°C

PARTICLE SIZE DISTRIBUTION

MESH	UM	RETAINED %
+30	+600	0
+40	+425	≤30
+45	+355	≥40
+45+50	+355+300	≥65
-60/PAN	-250	≤3

MAIN APPLICATIONS

- Bonded Abrasives and Coated abrasives
- Blasting,surface Treatment,Rust Removal
- Wet and dry blast media,grinding and polishing etc
- Floor/Wall laminates,Wear-resistant

...

PACKAGING:25kgs PVC bags+1MT big bag

The shown values are typical characteristics of the material and shall not be used to prepare specifications. They are submitted to tolerances of the production and meet the present standard of technique. We reserve our right for changes within the scope of technical progress or internal improvement..