

ZHENGZHOU HAIXU ABRASIVES CO.,LTD
EMAIL:SALES@ZZHAIXU.CN
MP/WECHAT/WHATSAPP:+8615838373120
WEBSITE:http://chinasic.net

TECHNICAL DATA SHEET

PRODUCT: GREEN SILICON CARBIDE

SIZE:F60

Green Silicon Carbide is produced in electrical internal resistance furnaces from silica sands and petroleum coke(added salt during smelting),with high hardness,thermal conductivity and strength.

AVERAGE CHEMICAL COMPOSITION(TYPICAL)

| | |
|--------------------------------|--------|
| SiC | ≥98.6% |
| C _F | ≤0.20% |
| Fe ₂ O ₃ | ≤0.40% |
| SiO ₂ | ≤0.05% |

PHYSICAL PROPERTIES(TYPICAL)

| | |
|----------------|------------------------|
| Density | ≥3.18g/cm ³ |
| Mohs Hardness | 9.4 |
| Magnetic | ≤0.0017% |
| Melting Point | 2250°C |
| Refractoriness | 1900°C |

PARTICLE SIZE DISTRIBUTION

| MESH | UM | RETAINED % |
|---------|----------|------------|
| +40 | +425 | 0 |
| +50 | +300 | ≤30 |
| +60 | +250 | ≥40 |
| +60+70 | +250+212 | ≥65 |
| -80/PAN | -180 | ≤3 |

MAIN APPLICATIONS

- Bonded Abrasives and Coated abrasives
- Blasting,surface Treatment,Rust Removal
- Wet and dry blast media,grinding and polishing etc
- Floor/Wall laminates,Wear-resistant

...

PACKAGING:25kgs PVC bags+1MT big bag

The shown values are typical characteristics of the material and shall not be used to prepare specifications. They are submitted to tolerances of the production and meet the present standard of technique. We reserve our right for changes within the scope of technical progress or internal improvement..