ZHENGZHOU HAIXU ABRASIVES CO.,LTD

EMAIL:SALES@ZZHAIXU.CN

MP/WECHAT/WHATSAPP:+8615838373120

WEBSITE:http://chinasic.net

# **TECHNICAL DATA SHEET**

**PRODUCT:** GREEN SILICON CARBIDE

**SIZE**:F100

Green Silicon Carbide is produced in electrical internal resistance furnaces from silica sands and petroleum coke(added salt during smelting), with high hardness, thermal conductivity and strength.

### **AVERAGE CHEMICAL COMPOSITION(TYPICAL)**

SiC	≥98.6%
$C_{F}$	≤0.20%
Fe <sub>2</sub> O <sub>3</sub>	≤0.40%
SiO <sub>2</sub>	≤0.05%

### **PHYSICAL PROPERTIES (TYPICAL)**

Specific Gravity  $\geq 3.95 \text{g/cm}^3$  Mohs Hardness 9.4 Melting Point 2250°C Refractoriness 1900°C

## **PARTICLE SIZE DISTRIBUTION**

MESH	UM	RETAINED %
+70	+212	0
+100	+150	≤20
+120	+125	≥40
+120+140	+125+106	≥65
+120+140+200	+125+106+75	*
-200/PAN	-75	≤3

#### **MAIN APPLICATIONS**

- -Bonded Abrasives and Coated abrasives
- -Blasting, surface Treatment, Rust Removal
- -Wet and dry blast media, grinding and polishing etc
- -Floor/Wall laminates, Wear-resistant

. . .

PACKAGING: 25kgs PVC bags+1MT big bag

The shown values are typical characteristics of the material and shall not be used to prepare specifications. They are submitted to tolerances of the production and meet the present standard of technique. We reserve our right for changes within the scope of technical progress or internal improvement..